



2511 Holman Avenue
 P. O. Box 80190
 Billings, Montana 59108-0190
 p: 406.652.3930; f: 406.652.3944
www.skgeotechnical.com

Date: July 11, 2017

Project: 16-3480L Laboratory Testing
 Aggregate Acceptance

Client: Mr. Fred Huppert
 Huppert Brothers Construction
 3509 54th Street West
 Billings, Montana 59106

Copies:

Source: Laurel South Quarry
Date Sampled: 5/17/17

Sample: Minus 1
Sampled by: FH/HB

Test Method	Lab Result	FP-14 705.02 Riprap Specification
Sodium Sulfate Soundness loss, <i>average of 3 coarse size ranges</i> (ASTM C 88)	---	12% max
Sodium Sulfate Soundness loss, <i>average of 4 fine size ranges</i> (ASTM C 88)	---	---
LA Abrasion loss, <i>crushed and sized to grading A</i> (ASTM C 535)	---	50% max
Freeze-Thaw loss, <i>recommend weighted average of 4 rocks of varying geology, through 30 cycles</i> (ASTM D 5312)	3.82% *	no FP-14 spec, but typ 10% max for those projects that specify
Specific Gravity, <i>recommend an average of 8 rocks of varying geology</i> (ASTM D 6473)	2.247 bulk Dry 2.324 bulk SSD 2.436 apparent 3.45% absorption	--- --- 2.40 min 4% max

* Freeze-Thaw photos attached on page 2.


 Joe B. DeBar, PE
 Materials Lab Manager

Date: July 11, 2017

Project: 16-3480L Laboratory Testing
Aggregate Acceptance

Client: Mr. Fred Huppert
Huppert Brothers Construction
3509 54th Street West
Billings, Montana 59106

Copies:

Source: Laurel South Quarry
Date Sampled: 5/17/17

Sample: Minus 1
Sampled by: FH/HB



Minus 1 samples before 30 freeze-thaw cycles.



Minus 1 samples after 30 freeze-thaw cycles.