



V-107 SEMI GLOSS HI SOLIDS DEEP TINT BASE

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION: V-107 Semi-Gloss Deep Base is an exceptional and durable interior/exterior alkyd semi gloss enamel, for general maintenance painting, and new construction. Formulated with special pigments and resin for excellent adhesion, and weathering resistance. These enamels can be manufactured in any gloss or color.

INTENDED USES: V-107 is formulated for use on properly prepared substrates such as metal. Its primary use is fast dry equipment enamel, where a semi-gloss, quality product is desired for extended durability. Other intended uses are for ornamental ironwork, structural steel, and construction equipment.

SURFACE PREPARATIONS: For best results, surface that is to be coated should be clean, dry, and free from any contamination. Coating shall be applied over a compatible rust inhibitive primer.

PHYSICAL INFORMATION

COLOR: SEMI CLEAR

GLOSS LEVEL: SEMI GLOSS

SOLIDS BY WEIGHT: 63%

RECOMMENDED DRY FILM THICKNESS: 1.5-2.0 MILS

THEORETICAL COVERAGE: 400-500 SQ FT PER GALLON

METHOD OF APPLICATION: AIRLESS SPRAY, AIR SPRAY, BRUSH, AND ROLLER

DRYING TIME @ 72 F

TO TOUCH: 30 Minutes

TO HANDLE: 60-90 Minutes

TO RECOAT: within 6 hours or after 5 days.

REGULATORY DATA

FLASHPOINT: 46 F

PRODUCT WEIGHT: 9.61 LB

MATERIAL VOC: 3.52 POUNDS PER GALLON / 422 GRAMS PER LITER

COATING VOC: 3.52 POUNDS PER GALLON / 422 GRAMS PER LITER

APPLICATION

MIXING: This material is a one-component coating and should always be mixed thoroughly with a power agitator before application.

MIX RATIO: Not applicable

WORKING POT LIFE: Not applicable

AIRLESS SPRAY: Recommended

Tip range 15-17 thou (0.38-0.43 mm)
Total output fluid pressure at spray tip not less than 2,500 p.s.i.

AIR SPRAY: Recommended
(Pressure Pot)

Gun	DeVilbiss	MBC or JGA
Air Cap	704	
Tip	E	

BRUSH: Suitable

Typically 1.5-2.0 mils can be achieved. Care should be taken to avoid under application.

ROLLER: Suitable

Typically 1.5-2.0 mils can be achieved. Care should be taken to avoid under application.

THINNER: Xylene

Do not thin more than allowed by local environmental legislation.

CLEANER: Xylene

WORK STOPPAGES: Thoroughly flush all equipment with xylene. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and / or viscosity increase of the material after storage. Material should be filtered prior to use.

CLEAN UP: Clean all equipment immediately with xylene. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations / legislation.

SYSTEM COMPATIBILITY

The following primers are recommended for V-107 ultra deep tint base.

Shop Coat Alkyd Primers

Universal Phenolic Primers

SHIPPING & STORAGE

NUMBER OF COMPONENTS: 1

PACKAGED IN: 55-Gallon Drums, 5 Gallon Pails, and 1 Gallon Cans

STORAGE TEMPERATURE: Minimum 20 F. Maximum 110 F.

TECHNICAL DATA SHEET

