

V-2870 SUPER SPEED BONDO GRAY

PRODUCT DESCRIPTION: V-2870 Super Speed Bondo Gray is a fast drying alkyd enamel for general purpose industrial use. This product features excellent gloss and color retention for interior and exterior exposure in mild to moderately corrosive environments. Dries to touch in 10 minutes air dry. These enamels can be manufactured in any gloss or color.

INTENDED USES: V-2870 is formulated for use on properly prepared substrates such as metal. Its primary use is fast dry equipment enamel, where a high gloss, quality product is desired for extended durability. Other intended uses are for ornamental ironwork, structural steel, and construction equipment.

SURFACE PREPERATIONS: For best results it is important that all surface contaminants, such as moisture, oil, dirt, rust and mil scale be removed before application. V-2870 can be applied to either blasted, hand or power tool cleaned steel. A minimum of SSPC-2 hand tool cleaning required.

PHYSICAL INFORMATION

COLOR: BONDO GRAY GLOSS: SEMI GLOSS SOLIDS BY WEIGHT: 71%

RECOMMENDED DRY FILM THICKNESS: 1.5-2.0 DFT
THEORETICAL COVERAGE: 350-450 SQ FT PER GALLON
METHOD OF APPLICATION: AIRLESS SPRAY OR AIR SPRAY

DRYING TIME @ 72 F

TO TOUCH: 15-30 MINUTES TO HANDLE: 60 MINUTES

TO RECOAT: WITHIN 6 HOURS OR AFTER 5 DAYS

REGULATORY DATA

FLASHPOINT: 63F

PRODUCT WEIGHT: 10.61LBS

MATERIAL VOC: 3.28 POUNDS PER GALLON / 394 GRAMS PER LITER COATING VOC: 3.45 POUNDS PER GALLON / 414 GRAMS PER LITER



APPLICATION

MIXING: This material is a one-component coating and should always be mixed thoroughly with a power agitator

before application.

MIX RATION: Not applicable

WORKING POT LIFE: Not applicable

AIRLESS SPRAY: Suitable Tip Range 15-17 thou (0.38-0.43mm)

total output fluid pressure at spray tip not less

than 2,500 P.S.I.

AIR SPRAY: Suitable Gun DeVilbiss MBC or JGA

(Pressure Pot) Air Cap 704

Tip E

BRUSH: Suitable Typically 1.5-2.0 mils can be achieved. Care

should be taken to avoid under application.

ROLLER: Suitable Typically 1.5-2.0 mils can be achieved. Care

should be taken to avoid under application.

THINNER: Xylene Do not thin more than allowed by local

environmental legislation when applicable.

CLEANER: Xylene

WORK STOPPAGES: Thoroughly flush all equipment with xylene. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or viscosity increase of the material after storage. Material should be filtered prior to use.

CLEAN UP: Clean all equipment immediately with xylene. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations legislation.

SYSTEM COMPATIBILTY:

The following primers are recommended for this topcoat

Universal Phenolic Primers

Epoxy ester Primers

SHIPPING & STORAGE

NUMBER OF COMPONENTS:

PACKAGED IN: 55-Gallon Drums, 5 Gallon Pails, and 1 Gallon Cans.

STORAGE TEMPERATURE: Minimum 20 F. Maximum 110F