

TECHNICAL DATA SHEET

Restora Concentrate Sealer is a 50/50 concentrated sealer suitable for concrete, metal & Colorbond® roof surfaces.

Dilute Restora Concentrate Sealer at a ratio of 50% concentrate sealer to 50% water for a standard sealer/primer (10L water in 10L concentrate sealer).

Once diluted, Restora Concentrate Sealer makes up a total of 40L of roof sealer.

For a medium build sealer/primer to use on porous surfaces, add 10L of water to 20L Restora Concentrate Sealer.

Restora Concentrate Sealer must not be used undiluted.

TYPICAL PROPERTIES

Colour	Clear
Number of Coats	1 minimum
Touch Dry	30 minutes
Overcoat	2 hours
Full Cure	14 days
<i>All figures are quoted at 25°C and 50% relative humidity</i>	
Coverage	8 m ² /L (once diluted*)
Dilution (Standard)	50% with water*
Dilution (Medium Build)	add 10L of water to 20L bucket*

Clean Up	Water
Application	Brush, Roll or Airless Spray
Tip Size	517
Components	1
Toxicity	Lead free. Dry film is non-toxic.
Dry Film (per coat)	39 µm
Size	20L buckets
Shelf Life	24 months

Note: *Restora Concentrate must not be used undiluted.

HEALTH & SAFETY

- **Contact Poisons Information Centre (Phone Australia: 13 11 26) or a doctor.**
- **IF SWALLOWED:** Rinse mouth. Do NOT induce vomiting.
- **IF ON SKIN:** Wash with plenty of soap and water.
- **IF INHALED:** Remove victim to fresh air and keep at rest in a position comfortable for breathing.
- **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
- **IF EXPOSED OR CONCERNED:** Get medical advice/attention.
- Wear appropriate protective clothing, gloves, eye/face protection and suitable respirator.

RECOMMENDATIONS & PRECAUTIONS

- Use this product in a well-ventilated area.
- Ensure that application is in accordance with Globalcote recommendations.
- Due care and consideration should be taken where water collection methods are present. Globalcote recommends allowing 14 days curing and an initial rinse (rain or tap water wash) prior to reconnecting water collection systems.
- The surface preparation is the responsibility of the Builder, Renovator, Contractor, or Applicator. It is also the responsibility of the Applicator to ensure that the substrate is of an acceptable standard prior to the application of the Globalcote Coating System.

TRAFFICABILITY: After full cure, Restora is suitable for light traffic during periodic service maintenance. Due care must be taken to avoid any damage (e.g., tools, equipment, or any sharp objects).

DISCLAIMER: The recommendations and data provided in this document are true and accurate at the time of testing. The information is given in good faith but without any guarantee as conditions and methods of use on the Globalcote product are beyond Globalcote's control. Globalcote recommends that the applicator of this product conducts a small test patch in an inconspicuous area to determine the suitability of the Globalcote material and its recommendations prior to use or application.