

Farblehm rot / *Color loam red* – T760



Chemische Analyse <i>Chemical analysis</i>		Mineralanalyse <i>Mineral analysis</i>	
SiO ₂	65,0 %	Kaolinit / <i>Kaolinite</i>	30 %
Al ₂ O ₃	21,7 %	Illit / <i>Illite</i>	22 %
TiO ₂	1,3 %	Quarz / <i>Quartz</i>	37 %
Fe ₂ O ₃	8,1 %	Sonstige / <i>Others</i>	11 %
CaO	0,5 %	Sedimentationsanalyse <i>Sedimentation analysis</i>	
MgO	4,2 %	< 63 µm	99,0 %
K ₂ O	2,4 %	< 20 µm	96,0 %
Na ₂ O	0,3 %	< 2 µm	76,0 %
Glühverlust <i>L.o.i.</i>	6,4 %		

Beschreibung <i>Description</i> Typische Anwendungen <i>Typical applications</i>	<p>Selektiv geförderter roter Ton, mahlgetrocknet <i>Selectively extracted red-coloured clay, dried by grinding</i></p> <ul style="list-style-type: none"> • Rote Lehmfarbe • Roter Lehmstreichputz • <i>Red-coloured clay paint</i> • <i>Red-coloured clay render</i> • Hohe Diffusionsoffenheit / Feuchtigkeitsregulierend • Schimmelhemmend • <i>Highly breathable / moisture-regulating</i> • <i>Mould-resistant</i>
Vorteile <i>Advantages</i>	

Weitere Daten / <i>Further data</i>	
Feuchtigkeit / <i>Moisture</i>	<1 %
Dichte / <i>Density</i>	2,6 g/cm ³
Schüttdichte / <i>Bulk density</i>	0,55 g/cm ³
pH-Wert / <i>ph value</i>	7-8
Farbe / <i>Color</i>	rot / <i>red</i>
Lieferform / <i>Delivery form</i>	
Pulver <i>Powder</i>	Lose <i>Lose</i>
	Big-Bag <i>Big-Bag</i>
	25kg-Papiersäcke <i>25kg Paper Bags</i>