



# COATINGS SOLUTIONS

## HIGH PERFORMANCE

[www.coatingsoln.com](http://www.coatingsoln.com) - Office: 863-450-2192- E-mail: [info@coatingsoln.com](mailto:info@coatingsoln.com)

# Technical Data Sheet

3150 Countyline Road STE 4  
Lakeland, FL 33811

## ACRYTHANE WB CONCRETE FLOOR ENAMEL

### DESCRIPTION:

Acrythane WB Concrete Floor Enamel is high solids penetrates and seals concrete balconies walkways, sidewalks and driveways. Also has good chemical resistance to gas oil and pool chemistry. Available in gallons and 5 gallon pails. Available in 2 premixed colors. two tint bases yield 16 colors

### ADVANTAGES:

- Clean and Seal in one day
- Hi-solids
- Quick Dry Walk on 24hrs
- Chemical and Stain Resistant
- Algae and Mold Inhibitor
- Inhibits weed growth
- VOC<150g/L

### SURFACE PREP:

Pressure wash ensuring that existing and exterior surfaces are clean and free of oil, efflorescence, laitance or contaminants prior to beginning the sealing process. Let substrate dry out overnight before sealing. Not compatible with damp substrate must be dry before sealing.

### COVERAGE:

Apply sealer between 175 to 300 sq. ft. per gallon; however, this rate will vary depending on the texture and absorption rate of the concrete being sealed

### APPLICATION INSTRUCTIONS:

Apply at temperatures between 50° F and 95° F. Do not apply if surface or ambient temperature is below 50°F. Don't apply if temperatures are expected to drop below freezing (32° F)

### MIXING:

A stir with a mechanical mixer a low speed for 2 minutes.

### APPLICATION:

Using a 3/16' nap solvent roller uniformly apply a coat of Acrythane Concrete Stain. Apply finish 2-4 hrs after first coat has cured. (Back rolling is recommended to eliminate puddling)**Warning recommended not to apply late in the afternoon when full sun on the deck will cause stain to get stringing on the roller**



**COATINGS SOLUTIONS**

**HIGH PERFORMANCE**

# Technical Data Sheet

3919 Airpark Drive STE 11-14

Lakeland, FL 33811

## DRY TIME:

Tack free/foot traffic: 2-4 hrs. Re coat 24 hrs. Heavy foot traffic 48 hrs. Vehicular Traffic 3 days.

If allowed to cure more than 24hrs. lightly sand the surface and wipe down with denatured alcohol or acetone before applying additional or finish coats.



*Remove Clean old Sealer*

## MAINTENANCE:

After sealer has cured 30 days deck can be maintained using a mild detergent or deck wash.

Reseal every 3-5 years depending on exposure and traffic.

## CLEANUP:

Immediately clean mixing blades with water

## STORAGE:

Store at temps above 50F. If product freezes, it is no longer usable. Shelf life is 18 months.

## WARRANTY:

Materials are free of defect. No labor



*After application of Acrythane Concrete Stain*