

## Triple C Manufacturing

Date                              11.16.10        1.14.11        3.15.11        4.29.11        3.15.12

Dry Film Thickness in mils / 2-3 mils desired

Number of Reads		20	50	20	35	50
Mil Thickness:	Average	2.22	2.01	2.13	2.17	1.8
	High	4.76	2.88	3.37	3.27	4.65
	Low	1.38	0.97	1.59	1.33	0.71

Comments: The average is down some from previous readings

We need to build a little more wet film to get the average over 2.00 mils.

Warmer temps will decrease paint thickness so a bit more attention to building more wet film is needed.

Overall the finish looks real good.