

Triple C Manufacturing

Date 3.15.12 4.26.12 5.30.12 6.20.12 8.30.12 12.10.10

Dry Film Thickness in mils / 2-3 mils desired

Number of Reads		50	50	50	50	50	50
Mil Thickness:	Average	1.8	2.67	3.42	2.36	2.49	2.02
	High	4.65	6.71	4.63	4.72	4.55	4.99
	Low	0.71	1.23	1.21	1.44	1.48	0.92

Comments: The average dft's look real good
Their were a couple of low areas on the flat sections.
Overall the finish looks real good.