

### Triple C Manufacturing

Date                                      1.24.13                      3.7.13                      4.23.13                      7.23.13

Dry Film Thickness in mils / 2-3 mils desired

Number of Reads		65	50	50	60
Mil Thickness:	Average	1.43	1.53	1.51	2.47
	High	3.04	3.51	2.76	3.55
	Low	0.76	0.43	0.49	1.64

**Comments:** All dft's are are much better and averages are within desired range  
Overall the finish looks real good.