



Finishing Recommendations

Account Name: Triple C Inc Date: 7/23/2013

Paint:

Product Code: IC-9626 Black Minion Acrylic

Reducing Solvents: Minion Reducers - Cold N-9059 (70 deg or lower)

Med N-9070 (70-90) Hot N-9090 (90+)

Applied Viscosity: 25-30" #2 Zahn Application Method: Conventional Air Spray

Equipment:

Fluid Pressure: 55-60 PSI Atomizing Air Pressure: 45-50 PSI

Tip or Nozzle Size: 0.055 Paint Heater Temp: N/A

Oven Type: Batch IR Oven Temp: N/A

Application:

Wet Film Thickness: 3-6 mils Dry Film Thickness: 1-2 mils per coat

Special Notes: