



## Finishing Recommendations

Account Name: Triple C Inc. Date: 7/23/2013

### Paint:

Product Code: VLX18462-01 3.5 VOC Gray Low HAP'S Ultra RI Primer

Reducing Solvents: MEK or MAK

Applied Viscosity: 25-30" #2 Zahn Application Method: Conventional Air Spray

### Equipment:

Fluid Pressure: 55-60 PSI Atomizing Air Pressure: 45-50 PSI

Tip or Nozzle Size: 0.055 Paint Heater Temp: N/A

Oven Type: Batch IR Oven Temp: N/A

### Application:

Wet Film Thickness: 2-4 mils Dry Film Thickness: 1-2 mils per coat

Special Notes: