



Class III Limestone

Alabaster Grove

Available Finishes



Brushed




Bush Hammered



Honed



Machine Sandblasted



Polished

Description

Alabaster Grove offers a soft, muted greige tone with hints of charcoal peppering offering a consistent texture and occasional marbling, making it a timeless choice for cut stone applications. Its high density and neutral palette allow it to blend seamlessly with a variety of materials and design styles - delivering both subtle elegance and lasting durability.

Physical Test Results

Absorption by Weight	0.50%
Compressive Strength	17,255 PSI
Modulus of Rupture	1,843 PSI
Flexural Strength.....	1,729 PSI
Density	168 lb/ft ³

Applications

Residential	Commerical
Interior	Exterior
Horizontal	Vertical

Printed reproductions are provided for reference only and may not accurately represent natural stone colors or characteristics.