

TUBING GRADE MECHANICAL PROPERTIES

Grade	Yield Strength (MPa)	Min Tensile (MPa)	Max Hardness (HRC)	Max Hardness (HBW)
J55	379 – 552	517	—	—
N80-1 / N80Q	552 – 758	689	—	—
L80-1 / L80-9Cr / L80-13Cr	552 – 655	655	23	241
C90-1 / C90-2	621 – 724	689	25.4	255
T95-1 / T95-2	655 – 758	724	25.4	255
P110	758 – 965	862	—	—