



GEOSYNTHETICS

CNM2199NT PRODUCT DATA SHEET

Our CNM2199NT woven geotextile is made of high tenacity monofilament polypropylene yarns, which are woven such that the yarns retain their relative position. Produced from first quality raw materials, these geotextiles offer optimum performance for use in reinforcement, stabilization and drainage applications. Our CNM2199NT resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13. Our CNM2199NT is NTPEP certified and meets requirements as per AASHTO Standards and/or D.O.T. Standards.

Properties	Test Method	English MARV ²	Metric MARV ²
MECHANICAL PROPERTIES			
Grab Tensile Strength (MD x CMD)	ASTM D4632	370 lbs x 250 lbs	1.65 kN x 1.11 kN
Grab Elongation (MD x CMD)	ASTM D4632	15% x 15%	
Trapezoidal Tear Strength	ASTM D4533	100 lbs x 60 lbs	0.445 kN x 0.267 kN
CBR Puncture Strength	ASTM D6241	950 lbs	4.28 kN
HYDRAULIC PROPERTIES			
Permittivity ³	ASTM D4491	0.3 sec ⁻¹	
Water Flow ³	ASTM D4491	18 gpm/ft ²	733 l/min/m ²
Percent Open Area (POA) ³	COE-02215	4%	
Apparent Opening Size (AOS) ^{3,4}	ASTM D4751	70 US Sieve	0.212 mm
ENDURANCE PROPERTY			
UV Stability	ASTM D4355	90% at 500 hours	
PACKAGING DETAILS			
Roll Width	Measured	12 ft	3.66 m
Roll Length	Measured	300 ft	91.5 m
Roll Area	Measured	400 yd ²	335 m ²
Roll Weight	Measured	205 lbs	93 kg
AASHTO CLASSIFICATION			
M288 Survivability Class		2 & 3	
M288 Application ⁵		D, E	

NOTE

¹ The property values listed above are subject to change without notice

² Minimum Average Roll Value (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above. All values are MARV unless otherwise noted.

³ At time of manufacturing. Handling may change these properties.

⁴ Maximum Average Roll Value

⁵ S/F=Silt Fence, SP=Separation, ST=Stabilization, D=Drainage, E=Erosion Control, SS=Subgrade Stabilization

Disclaimer: This information describes product properties at the time of manufacture and testing only and does not constitute or confer any warranties. Values stated will be affected over time by handling, storage, shipping, installation, use and other factors. Core & Main Geosynthetics does not provide engineering advice with respect to product use herein or otherwise and will not be liable for installation error. CORE & MAIN GEOSYNTHETICS DISCLAIMS ALL IMPLIED WARRANTIES, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY.

Local Knowledge
Local Experience
Local Service, Nationwide®

Core & Main Geosynthetics
P. O. Box 640 Willacoochee, GA 31650
Direct Phone: 912-534-6071 **Toll Free:** 800-948-7870
coreandmain.com/geosynthetics