



GEOSYNTHETICS

CNM770HP PRODUCT DATA SHEET

Our CNM770HP woven geotextile is made of high tenacity monofilament and fibrillated tape polypropylene yarns, which are woven such that the yarns retain their relative position. Produced from first quality raw materials, these geotextiles offer optimum performance for use in reinforcement, stabilization and drainage applications. Our CNM770HP resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13.

Properties	Test Method	English MARV ²	Metric MARV ²
MECHANICAL PROPERTIES			
Grab Tensile Strength (MD x CMD)	ASTM D4632	600 lbs x 500 lbs	2.67 kN x 2.23 kN
Grab Elongation (MD x CMD)	ASTM D4632	12 % x 6 %	12 % x 6 %
Wide Width Tensile Strength Ultimate (MD x CMD)	ASTM D4595	7200 lbs/ft x 5760 lbs/ft	105.1 kN/m x 84 kN/m
Wide Width Tensile Strength @ 5% (MD x CMD)	ASTM D4595	3200 lbs/ft x 3200 lbs/ft	52.5 kN/m x 52.5 kN/m
Wide Width Tensile Strength @ 2% (MD x CMD)	ASTM D4595	1140 lbs/ft x 1560 lbs/ft	16.6 kN/m x 22.8 kN/m
Trapezoidal Tear Strength	ASTM D4533	250 lbs x 220 lbs	1.11 kN x 0.89 kN
CBR Puncture Strength	ASTM D6241	1900 lbs	8.44 kN
HYDRAULIC PROPERTIES			
Permittivity ³	ASTM D4491	0.90 sec ⁻¹	
Water Flow ³	ASTM D4491	30 gpm/ft ²	1222 l/min/m ²
Apparent Opening Size (AOS) ^{3,4}	ASTM D4751	20 US Sieve	0.85 mm
ENDURANCE PROPERTY			
UV Stability	ASTM D4355	80% at 500 hours	
PACKAGING DETAILS			
Roll Width	Measured	15 ft	4.6 m
Roll Length	Measured	300 ft	91.5 m
Roll Area	Measured	500 yd ²	418 m ²

NOTE

¹ The property values listed above are subject to change without notice

² Minimum Average Roll Value (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above. All values are MARV unless otherwise noted.

³ At time of manufacturing. Handling may change these properties.

⁴ Maximum Average Roll Value

Disclaimer: This information describes product properties at the time of manufacture and testing only and does not constitute or confer any warranties. Values stated will be affected over time by handling, storage, shipping, installation, use and other factors. Core & Main Geosynthetics does not provide engineering advice with respect to product use herein or otherwise and will not be liable for installation error. CORE & MAIN GEOSYNTHETICS DISCLAIMS ALL IMPLIED WARRANTIES, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY.

Local Knowledge
Local Experience
Local Service, Nationwide®

Core & Main Geosynthetics
P. O. Box 640 Willacoochee, GA 31650
Direct Phone: 912-534-6071 **Toll Free:** 800-948-7870
coreandmain.com/geosynthetics