EARTH SAVER
GEOSYNTHETICS & EROSION CONTROL PRODUCTS

ES-2SRD

ES-2SRD – a Double Net Straw Blanket is a temporary Erosion Control Blanket is composed of a 100% weed free agricultural straw matrix mechanically stitch bonded with a photodegradable polypropylene thread (white) to two (2) polypropylene photodegradable (white) nets which are located at the top and bottom of the blanket. ES-2SRD is recommended for applications requiring erosion protection for a period of up to 3 months. The material is fully degradable. The net and thread are photodegradable, and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions. ES-2SRD is made in the USA.

Index Property	Test Method	Value	
Mass Per Unit Area	ASTM D6475	6.5 oz/sy	220 g/m^2
Thickness	ASTM D6525	259 mils	6.1 mm
Tensile Strength MD	ASTM D6818	140 lbs/ft	1.7 kN/m
Tensile Strength TD	ASTM D6818	110 lbs/ft	1.3 kN/m
Bench Scale Tests			
Soil Loss Ratio[1]	ASTM D7101	9.76	
Permanent Shear Stress[1]	ASTM D7207	1.24 psf	
Light Penetration[1]	ASTM D6567	20.6%	
Biomass Improvement[1]	ASTM D7322	PASS>100%	
Design Parameters			
Unvegetated RUSLE C-Factor[1,2]	ASTM D6459	0.012	
Maximum Slope Gradiant		2H:1V	
Unvegetated permissable shear strength[1,2]	ASTM D6460	1.94 psf	
Unvegetated permissable velocity[1,2]	ASTM D6460	8.5 ft/sec	
Manning's Roughness "n" (HEC-15)			
τ_{lower}	τ_{mid}	τ_{upper}	
0.05	0.036	0.032	

Physical Description				
Netting- top net	0.52" x 0.5" photodegradable PP (white)			
-bottom net	0.52" x 0.5" photodegradable PP (white)			
Thread	300 denier degradable PP (white)			
Matrix	100% agricultural cured wheat straw, 0.5 lbs/sy			
Packaging Details				
Roll Width	8 ft	2.4 m	16 ft	4.9 m
Roll Length	112.5 ft	34.3 m	562.5 ft	171.5 m
Roll Area	100 yd^2	83.6 m^2	1000 yd^2	840 m^2
Roll Weight	50 lbs	23 kg	500 lbs	230 kg
Packaging specifics	All rolls are wrapped tightly with stretch wrap to protect the erosion control product from weather and elements			
Classification				
FHWA	Type 2.D			
ECTC	Type 2.D			
AASHTO	Type 2A2			
Functional Longevity	12 months			

1- Values developed by TRI/Environmental Inc. using Bench Scale and Large Scale testing for AASHTO's National Transportation Product Evaluation Program

2-Generalized for typical applications, based on hydraulic performance with ASTM D6459 and D6460 tests.

IECA International Erosion Control Association
Protecting Soil and Water Resources

EROSION CONTROL TECHNOLOGY COUNCIL
ECTC - EST 1992

PRODUCT EVALUATION & AUDIT DATAMINE TESTED

Local Knowledge
Local Experience
Local Service, Nationwide®

Core & Main Geosynthetics
Direct Phone: 912-534-6071 Toll Free: 800-948-7870
coreandmain.com/geosynthetics