LANDLOK® TRM

Product Data

LANDLOK® 455

LANDLOK® 455 turf reinforcement mat (TRM) features X3® technology that consists of a dense web of crimped, interlocking, multi-lobed polypropylene fibers positioned between two biaxially oriented nets and mechanically bound together by parallel stitching with polypropylene thread. The TRM is designed to accelerate seedling emergence, exhibit high resiliency, and possess strength and elongation properties to limit stretching in a saturated condition. Every component of LANDLOK® 455 is stabilized against chemical and ultraviolet degradation which are normally found in a natural soil environment. Furthermore, the TRM contains no biodegradable components.

LANDLOK® 455 conforms to the property values listed below[1] and is manufactured at a Propex facility having achieved ISO 9001:2008 certification. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured		100%	100%
PHYSICAL			
Mass/Unit Area [2]	ASTM D-6566	12.0 oz/yd²	407 g/m²
Thickness [2]	ASTM D-6525	0.50 in	12.7 mm
Light Penetration (% Passing) [2]	ASTM D-6567	20%	20%
Color	Visual	Green	
MECHANICAL			
Tensile Strength [2]	ASTM D-6818	425 x 350 lbs/ft	6.2 x 5.1 kN/m
Elongation [2]	ASTM D-6818	50%	50%
Resiliency [2]	ASTM D-6524	90%	90%
Flexibility [2]	ASTM D-6575	0.030 in-lb	34,615 mg-cm
ENDURANCE			
UV Resistance % Retained at 1,000 hrs [2]	ASTM D-4355	80%	80%
ROLL SIZES		8 ft x 125 ft 16 ft x 125 ft	2.45 m x 38.1 m 4.88 m x 38.1 m

NOTES:

1. The property values listed above are effective 07/22/2019 and are subject to change without notice.
2. Values represent testing at time of manufacture and are shown as typical values.
3. Maximum permissible velocity and shear stress has been obtained through vegetated testing programs featuring specific soil types, vegetation classes, flow conditions, and failure criteria. These conditions may not be relevant to every project nor are they replicated by other manufacturers. Please contact Propex for further information.
4. Calculated as typical values from large-scale flexible channel lining test programs with a flow depth of 6 to 12 inches.

Distributed By:

L & M Supply Co., Inc.
P. O. Box 640 - Willacoochee, GA 31650
912-534-6071 Direct
800-948-7870 Toll Free
www.landmsupplyco.com

Propex GEOSOLUTIONS

Propex Operating Company, LLC · 4019 Industry Drive · Chattanooga, TN 37416

ARMORMAX®, PYRAMAT®, LANDLOK®, X3®, PYRAWALL®, SCOURLOK®, GEOTEX®, PETROMAT®, PETROTAC®, REFLECTEX®, and GRIDPRO™ are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.

© 2019 Propex Operating Company, LLC