

## Multi-Rib & PBR/R

The WeatherXL™ Siliconized Modified Polyester coil coatings from Sherwin-Williams are ideal for agricultural, industrial, and pre-engineered metal building components and systems.

- Recognized for its remarkable color and gloss retention as well as its superior chalk resistance.
- A two-coat system that is highly resistant to stains, abrasion and metal marking.

### Solar Reflectivity (SR) and Solar Reflectance Index (SRI) by Color

**Solar reflectivity** or reflectance is the ability of a material to reflect solar energy from its surface back into the atmosphere. The SR value is a number from 0 to 1.0. A value of 0 indicates that the material absorbs all solar energy and a value of 1.0 indicates total reflectance.

The **Solar Reflectance Index** is used for compliance with **LEED** requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. Emissivity is a material's ability to release absorbed energy.



**SHERWIN-WILLIAMS**  
 Coil Coatings

**WeatherXL™**

Sherwin-Williams® and WeatherXL™ are trademarks of SWIMC LLC.



Ash Gray  
 SR 0.46 | SRI 52



Burnished Slate  
 SR 0.34 | SRI 35



Charcoal Gray  
 SR 0.37 | SRI 39



Colony Green ▲  
 SR 0.28 | SRI 27



Desert Sand  
 SR 0.42 | SRI 47




Evergreen  
 SR 0.35 | SRI 37



Black ▲  
 SR 0.31 | SRI 31



Hawaiian Blue ▲  
 SR 0.31 | SRI 31



Koko Brown  
 SR 0.35 | SRI 37



Light Stone  
 SR 0.56 | SRI 65



Polar White  
 SR 0.64 | SRI 77



Rustic Red  
 SR 0.36 | SRI 38



Saddle Tan  
 SR 0.47 | SRI 53



Copper Metallic ▲  
 SR 0.51 | SRI 58

▲ Only 26 ga.