

TEST REPORT PREPARED FOR DRAGON PORTLAND CEMENT

REPORT REFERENCE	DPL CPC	63
CLIENT REFERENCE	DP01 CPC 04-26 52.5N	
SAMPLE	CEM I 52.5N	
SEAL NUMBER	B445289	
SAMPLE DATE	07-Aug-26	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	11-Aug-26	
DATE OF TESTS	11-Aug-26	to 08-Sep-26
DATE OF REPORT	08-Sep-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	205 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	36.8 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	65.4 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	3.00 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.35 %	(BSEN 196-2:2013)
SULPHATE	3.16 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**