

TEST REPORT PREPARED FOR DRAGON PORTLAND CEMENT

REPORT REFERENCE	DPL 42	2
CLIENT REFERENCE	DP19 CPC 04-03 CEM111 A 40%GGBS 42.5N	
SAMPLE	CEM III/A 42.5N	
SEAL NUMBER	B445213	
SAMPLE DATE	07-Aug-26	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	11-Aug-26	
DATE OF TESTS	11-Aug-26	to 08-Sep-26
DATE OF REPORT	08-Sep-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	198 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	14.8 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	56.6 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI (CORRECTED)	4.36 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	1.09 %	(BSEN 196-2:2013)
SULPHATE	2.69 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**