

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	PC	10
CLIENT REFERENCE	CPC/DPL/42/11-26 4/6/26	
SAMPLE	CEM111/A 42.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	09-Jun-26	
DATE OF TESTS	10-Jun-26	to 08-Jul-26
DATE OF REPORT	21-Jul-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	183 mins	> Or = 60 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	17.8 MPa	>Or = 10 Mpa
AT 28 DAYS	57.6 MPa	> Or = 42.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

INSOLUBLE RESIDUE	1.20 %	< Or = 5.0%
SULPHATE	2.67 %	< Or = 3.5%
LOI (CORRECTED)	3.88 %	< Or = 5.0%

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**