

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	PC	15
CLIENT REFERENCE	CPC/DPL/42/17-26 17/7/26	
SAMPLE	CEM111/A 42.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	22-Jul-26	
DATE OF TESTS	22-Jul-26	to 19-Aug-26
DATE OF REPORT	19-Aug-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	166 mins	> Or = 60 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	17.1 MPa	>Or = 10 Mpa
AT 28 DAYS	54.3 MPa	> Or = 42.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

INSOLUBLE RESIDUE	1.84 %	< Or = 5.0%
SULPHATE	2.72 %	< Or = 3.5%
LOI (CORRECTED)	4.34 %	< Or = 5.0%

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**