

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	PC	20
CLIENT REFERENCE	CPC/DPL/42/23-26 25/8/26	
SAMPLE	CEM111/A 42.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	26-Aug-26	
DATE OF TESTS	27-Aug-26	to 24-Sep-26
DATE OF REPORT	29-Sep-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	211 mins	> Or = 60 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	17.9 MPa	>Or = 10 Mpa
AT 28 DAYS	55.6 MPa	> Or = 42.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

INSOLUBLE RESIDUE	1.08 %	< Or = 5.0%
SULPHATE	2.68 %	< Or = 3.5%
LOI (CORRECTED)	4.45 %	< Or = 5.0%

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**