

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	PC	21
CLIENT REFERENCE	CPC/DPL/42/24-26 3/9/26	
SAMPLE	CEM111/A 42.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	07-Sep-26	
DATE OF TESTS	08-Sep-26	to 06-Oct-26
DATE OF REPORT	05-Oct-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	205 mins	> Or = 60 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	19.1 MPa	>Or = 10 Mpa
AT 28 DAYS	58.0 MPa	> Or = 42.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

INSOLUBLE RESIDUE	1.13 %	< Or = 5.0%
SULPHATE	2.94 %	< Or = 3.5%
LOI (CORRECTED)	3.10 %	< Or = 5.0%

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**