

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	PC	20
CLIENT REFERENCE	CPC/DPL/42/021 15/8/25	
SAMPLE	CEM I 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	20-Aug-25	
DATE OF TESTS	20-Aug-25	to 19-Sep-25
DATE OF REPORT	18-Sep-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	205 mins	> Or = 45 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	31.9 MPa	>Or = 30 Mpa Mpa
AT 28 DAYS	57.6 MPa	> Or = 52.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

SULPHATE	3.09 %	< Or = 4.0%

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**