

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	DPL 52	467
CLIENT REFERENCE	CPC/DPL/52/30-26 29/7/26	
SAMPLE	CEM I 52.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	31-Jul-26	
DATE OF TESTS	31-Jul-26	to 28-Aug-26
DATE OF REPORT	01-Sep-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	201 mins	> Or = 45 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	40.3 MPa	>Or = 30 Mpa Mpa
AT 28 DAYS	67.3 MPa	> Or = 52.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

LOI	2.76 %	< Or = 5.0%
INSOLUBLE RESIDUE	0.51 %	< Or = 5.0%
SULPHATE	3.26 %	< Or = 4.0%

END OF REPORT

SIGNED:.....

Certificate signed by: S.Sykes
Senior Technician

Date 29.09.21