

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	DPL 52	437
CLIENT REFERENCE	CPC/DPL/485 14/11/25	
SAMPLE	CEM I 52.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	17-Nov-25	
DATE OF TESTS	17-Nov-25	to 15-Dec-25
DATE OF REPORT	12-Feb-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	155 mins	> Or = 45 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	36.8 MPa	>Or = 30 Mpa Mpa
AT 28 DAYS	64.5 MPa	> Or = 52.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

LOI	2.81 %	< Or = 5.0%
INSOLUBLE RESIDUE	0.95 %	< Or = 5.0%
SULPHATE	3.20 %	< Or = 4.0%

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician

Date

29.09.21