

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	DPL 52	460
CLIENT REFERENCE	CPC/DPL/52/22-26 SILO 2 4/6/26	
SAMPLE	CEM I 52.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	09-Jun-26	
DATE OF TESTS	10-Jun-26	to 08-Jul-26
DATE OF REPORT	08-Jul-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	196 mins	> Or = 45 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	35.8 MPa	>Or = 30 Mpa Mpa
AT 28 DAYS	67.2 MPa	> Or = 52.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

LOI	2.86 %	< Or = 5.0%
INSOLUBLE RESIDUE	0.72 %	< Or = 5.0%
SULPHATE	3.06 %	< Or = 4.0%

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**