

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	DPL 52	465
CLIENT REFERENCE	CPC/DPL/52/28-26 17/7/26	
SAMPLE	CEM I 52.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	22-Jul-26	
DATE OF TESTS	22-Jul-26	to 19-Aug-26
DATE OF REPORT	19-Aug-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	205 mins	> Or = 45 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	37.6 MPa	>Or = 30 Mpa Mpa
AT 28 DAYS	67.8 MPa	> Or = 52.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

LOI	2.69 %	< Or = 5.0%
INSOLUBLE RESIDUE	0.40 %	< Or = 5.0%
SULPHATE	3.20 %	< Or = 4.0%

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician

Date

29.09.21