

TEST REPORT PREPARED FOR PORTLAND CEMENT

REPORT REFERENCE	DPL 52	469
CLIENT REFERENCE	CPC/DPL/52/33-26 20/8/26	
SAMPLE	CEM I 52.5N	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	21-Aug-26	
DATE OF TESTS	25-Aug-26	to 22-Sep-26
DATE OF REPORT	29-Sep-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	207 mins	> Or = 45 mins
----------------------	----------	----------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	34.7 MPa	>Or = 30 Mpa Mpa
AT 28 DAYS	65.3 MPa	> Or = 52.5

CHEMICAL COMPOSITION EN196-2013 :- by mass, as received

LOI	3.10 %	< Or = 5.0%
INSOLUBLE RESIDUE	0.46 %	< Or = 5.0%
SULPHATE	3.09 %	< Or = 4.0%

END OF REPORT

SIGNED:.....

Certificate signed by: S.Sykes
Senior Technician

Date 29.09.21