PAC-CLAD Color Availability

	Reflectivity Emissivity 3 Yr Exposure SRI*				Steel		Aluminum			
PAC-CLAD Cool Colors			3 Yr Exposure	SRI*	24 ga.	22 ga.	.032	.040	.050	.063
Almond	0.56	0.89	0.57	66	•	•	•	•	•	
Bone White	0.73	0.89	0.71	89			•		•	•
Cardinal Red	0.37	0.89	0.38	41	•				•	
Charcoal	0.28	0.89		29	•					
Colonial Red	0.32	0.89		34	•		•		•	
Dark Bronze	0.25	0.89		25	•	•	•	•	•	•
Evergreen	0.26	0.88		26	•		•			
Granite	0.36	0.89	0.35	40	•*	•	•*	•	•*	
Hemlock Green	0.30	0.90		32	•	•	•		•	
Hunter Green	0.26	0.88		26	•		•			
Mansard Brown	0.25	0.88		25	•	•	•	•	•	
Medium Bronze	0.27	0.90		28	•	•	•	•	•	•
Military Blue	0.34	0.88		36	•		•			
Musket Gray	0.31	0.89		33	•	•	•		•	
Patina Green	0.34	0.89		37	•		•			
Sandstone	0.53	0.89	0.49	62	•	•	•	•	•	•
Sierra Tan	0.36	0.89	0.35	40	•	•	•	•	•	
Slate Blue	0.26	0.87		26	•		•			
Slate Gray	0.36	0.89		40	•	•	•	•	•	
Stone White	0.64	0.88	0.59	77	•	•	•	•	•	•
Teal	0.26	0.88		26	•		•			
Terra Cotta	0.36	0.89	0.37	40	•		•		•	
Matte Black**	0.25	0.85		23	•		•	•	•	•
PAC-CLAD Metallic										Or The Control
Aged Copper	0.28	0.89		29	•		•		•	
Champagne	0.41	0.80	0.40	43	•		•		•	
Copper Penny	0.49	0.87	0.47	56	•		•		•	
Silver	0.60	0.83	0.55	70	•		•	•	•	
Weathered Zinc	0.30	0.81		28	•		•		•	
Zinc	0.32	0.89	0.31	34	•		•		•	
PAC-CLAD Standar	rd Colors (d		cool roof requi	rements)	7/11/1997	AND AND A SECOND	Grand Control	TOTAL 1988		
Arcadia Green					•		•			
Award Blue							•		•	
Berkshire Blue					•*					
Burgundy					•		•			
Forest Green					•	•	•	•	•	
Hartford Green										
Interstate Blue										

PAC-CLAD® Metallic finishes are available from stock at a moderate extra cost. PAC-CLAD® Copper Penny is a Non-Weathering finish. *Solar Reflectance Index calculated according to ASTM E-1980. **Matte Black (SRI Color) in steel only.

Energystar® Performance Criteria Emissivity uses ASTM C1371/E408. Reflectivity uses ASTM E903/C1549.

Installation

PAC-CLAD® can be cut, formed, nailed, screwed, or riveted using hand or power tools. Fabricate and install in accordance with drawings and normal sheet metal practices using hand or power tools. Keep cutting edges sharp, clean, and properly aligned. Exercise care during fabrication and installation to avoid damage.

Maintenance

Maintenance is not required. This finish is a member of the Teflon[®] family, and is self-cleaning. If cleaning is desired, it can be washed with a mild soap and water followed by a clean-water rinse.

These color reproductions are as accurate as modern printing technology will permit. Free material samples are available on request.

PAC-CLAD® is available with a smooth texture or a standard E-5 stucco embossed pattern, available at extra cost. *Low Gloss/Low Sheen

This finish is a full Kynar 500[®]/Hylar 5000[®] finish, but is formulated in a **low gloss/low sheen** in order to minimize the appearance of oil-canning.

- Technical Data for Kynar 500[®]/Hylar 5000[®] Coating
 •Life Expectancy—20 years exposure— Chalk: rating of 8 or better. Color: 5ΔE (Hunter Units) change.
- •Accelerated Weathering—(ASTM G-23 Type EH) 5,000 hours Chalk: rating of 8 or better. Color: ≤5ΔE (Hunter Units) color change
- •Humidity Resistance-(ASTM 2247) 2,000 hours No change in pencil hardness.
- •Salt Spray Resistance (ASTM B 117) 2,000 hours for Aluminum, creepage at scribe ≤1/32", no blisters. 2,000 hours for hot dipped Galvanized, creepage at scribe 1/8", few #8 blisters.

- Chemical/Acid Pollution Resistance—(ASTM D 1808) - Pass.
- •Solvent Resistance—(NCCA procedure 11-18, no comparable ASTM test) Pass.
- Formability—(ASTM D 3281 and ASTM D 1737) -Can be formed without film fracture using normal metal shop practices to a 1 to 2-T bend radius
- •Hardness-(ASTM D 3363) ≥F pencil hardness.
- •Gloss-30 ± 5 at 60° (low gloss/sheen available).
- •Abrasion Resistance-(ASTM D 968) Coefficient of
- •Adhesion—(ASTM D 3359 and NCCA procedure No.
- •Impact Resistance—(ASTM D 2794 and NCCA Technical Bulletin No. 11-6) - 70 inch/lbs., no tape pick-off.

- Recycled Content

 PAC-CLAD Aluminum 91%
- •PAC-CLAD Steel 28 to 35%



2810 Old Willow Road Northbrook, IL 60062 847-729-9292 847-729-0340 Fax

126 S. MacDonald Avenue Joliet, IL 60431 815-725-3030 815-725-3344 Fax

PAC-CLAD® is a registered trademark of Petersen Aluminum Corporation, Kynar 500® is a registered trademark of Eli Atochem North America, Inc. Hylar 5000® is a registered trademark of Ausimont USA.

8/2006