

CERAMICHEitaliane®



ENZO S.TONE



Ph. Mott-Artz

I.Stone LIGHT

I.Stone GREY

CERAMICHEitaliane®

I.Stone CREAM

# LIGHT

Gres Porcellanato Porcelain Stoneware  
60x120 24"x48" | 60x60 24"x24" | 16,2x32,5 6,38"x12,80"



I.STONE LIGHT 60x120 24"x48" | 60x60 24"x24"

# GREY

Gres Porcellanato Porcelain Stoneware  
60x120 24"x48" | 60x60 24"x24" | 16,2x32,5 6,38"x12,80"



I.STONE  
GREY  
60x120 24"x48"



# CREAM

Gres Porcellanato Porcelain Stoneware  
60x120 24"x48" | 60x60 24"x24" | 16,2x32,5 6,38"x12,80"



I.STONE CREAM 60x60 24"x24"



**60×120** 24"x48" **R10**  
**± 9,5 mm**  
YA1941RT I.STONE IN **Light** Rett.  
YA1941RT I.STONE IN **Grey** Rett.  
YA1941RT I.STONE IN **Cream** Rett.

**16,2×32,5** 6,38"x12,80" **R10**  
**± 8,5 mm**  
EA1826NT I.STONE IN **Light** Rett.  
EA1827NT I.STONE IN **Grey** Rett.  
EA1829NT I.STONE IN **Cream** Rett.

**60×60** 24"x24" **R10**  
**± 8,5 mm**  
EA1921RT I.STONE IN **Light** Rett.  
EA1922RT I.STONE IN **Grey** Rett.  
EA1923RT I.STONE IN **Cream** Rett.

**60×60** 24"x24" **R11**  
**± 8,5 mm**  
EA1921OURT I.STONE OUT **Light** Rett.  
EA1922OURT I.STONE OUT **Grey** Rett.  
EA1923OURT I.STONE OUT **Cream** Rett.

PESI E MISURE / WEIGHT AND SIZES / GEWICHTE UND VERPACKUNGEN

| dimensioni<br>sizes<br>abmessungen | spessore<br>thickness<br>stärke | pz/collo<br>pcs/box<br>stk/ktn | mq/collo<br>sqm/box<br>qm/ktn | kg/collo<br>kg/box<br>kg/ktn | colli/pallet<br>box/pallet<br>ktn/pallet | mq/pallet<br>sqm/pallet<br>qm/pallet | kg/pallet<br>kg/pallet<br>kg/pallet |
|------------------------------------|---------------------------------|--------------------------------|-------------------------------|------------------------------|------------------------------------------|--------------------------------------|-------------------------------------|
| 60×120 Rettificato R10             | 9,5 mm                          | 2                              | 1,44                          | 29,50                        | 36                                       | 51,84                                | 1062,00                             |
| 60×60 Rettificato R10 / R11        | 8,5 mm                          | 4                              | 1,44                          | 28,50                        | 32                                       | 46,08                                | 912,00                              |
| 16,2×32,5 Rettificato R10          | 8,5 mm                          | 23                             | 1,21                          | 22,00                        | 60                                       | 72,60                                | 1320,00                             |

CARATTERISTICHE TECNICHE

TECHNICAL FEATURES / TECHNISCHE EIGENSCHAFTEN

NORMA DI RIFERIMENTO / SPECIFICATION REFERENCE

EN 14411 ISO 13006 GRUPPO BLA ANNEX G

| Caratteristica tecnica<br>Technical feature                                         |                                                                                                     | Norma<br>Norm           | Rettificato*<br>Rectified*                                                                    | I.STONE<br>60×120   60×60 |
|-------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------|-------------------------|-----------------------------------------------------------------------------------------------|---------------------------|
|    | LUNGHEZZA E LARGHEZZA - LENGTH AND WIDTH                                                            | UNI EN ISO 10545/2      | ± 0,3% max 1mm                                                                                | CONFORME<br>COMPLIANT     |
|                                                                                     | SPESSORE - THICKNESS                                                                                |                         | ± 5 % max 0,5mm                                                                               |                           |
|                                                                                     | RETTILINEITÀ DEI LATI - STRAIGHTNESS OF SIDES                                                       |                         | ± 0,3% max 0,8mm                                                                              |                           |
|                                                                                     | ORTOGONALITÀ - WEDGING                                                                              |                         | ± 0,3% max 1,5mm                                                                              |                           |
|                                                                                     | PLANARITÀ - FLATNESS                                                                                | *According to ISO 13006 | ± 0,4% max 1,8mm                                                                              |                           |
|    | ASSORBIMENTO ACQUA IN %<br>% WATER ABSORPTION                                                       | UNI EN ISO 10545/3      | ≤ 0,5 %                                                                                       | CONFORME<br>COMPLIANT     |
|    | FORZA DI ROTTURA<br>BREAKING STRENGTH                                                               |                         | > 1300 N                                                                                      | > 1350 N                  |
|                                                                                     | MODULO DI ROTTURA – MODULUS OF RUPTURE<br>NOT APPLICABLE TO TILES WITH BREAKING<br>STRENGHT ≥3000 N | UNI EN ISO 10545/4      | ≥ 35 N/MM²                                                                                    | ≥ 45*<br>*average value   |
|    | RESISTENZA ALL'ABRASIONE<br>RESISTANCE TO SURFACE ABRASION                                          | UNI EN ISO 10545/7      | PEI<br>Solo per piastrelle smaltate<br>Only for glazed tiles                                  | PEI 4                     |
|    | RESISTENZA AGLI SBALZI TERMICI<br>THERMAL SHOCKS RESISTANCE                                         | UNI EN ISO 10545/9      | NESSUN CAMPIONE DEVE<br>PRESENTARE DIFETTI VISIBILI<br>NO SAMPLE MUST SHOW<br>VISIBLE DEFECTS | CONFORME<br>COMPLIANT     |
|   | RESISTENZA AL GELO<br>FROST RESISTANCE                                                              | UNI EN ISO 10545/12     | RESISTENTI - RESISTANT                                                                        | CONFORME<br>COMPLIANT     |
|  | RESISTENZA ALLE MACCHIE<br>STAIN RESISTANCE                                                         | UNI EN ISO 10545/14     | GL ≥ 3                                                                                        | Classe 3                  |
|  | SCIVOLOSITÀ<br>SLIP RESISTANCE                                                                      | DIN 51130               | Dichiarare un valore (R)<br>Declare a value (R)                                               | R10 – R11                 |
|  | RESISTENZA AL FUOCO<br>FIRE RESISTANCE                                                              | UNI EN ISO 13501/1      | CLASSE A1 OPPURE A1 <sub>FL</sub><br>CLASS A1 OR A1 <sub>FL</sub>                             | A1 <sub>FL</sub>          |

| Caratteristica tecnica<br>Technical feature                                           |                                                                                                     | Norma<br>Norm           | Non Rettificato<br>Not Rectified                                                              | Rettificato*<br>Rectified* | I.STONE<br>16,2×32,5    |
|---------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------|-------------------------|-----------------------------------------------------------------------------------------------|----------------------------|-------------------------|
|    | LUNGHEZZA E LARGHEZZA - LENGTH AND WIDTH                                                            | UNI EN ISO 10545/2      | ± 0,6% max 2mm                                                                                | N/A                        | CONFORME<br>COMPLIANT   |
|                                                                                       | SPESSORE - THICKNESS                                                                                |                         | ± 5 % max 0,5mm                                                                               |                            |                         |
|                                                                                       | RETTILINEITÀ DEI LATI - STRAIGHTNESS OF SIDES                                                       |                         | ±0,5% max 1,5 mm                                                                              |                            |                         |
|                                                                                       | ORTOGONALITÀ - WEDGING                                                                              |                         | ±0,5% max 2mm                                                                                 |                            |                         |
|                                                                                       | PLANARITÀ - FLATNESS                                                                                | *According to ISO 13006 | ±0,5% max 2mm                                                                                 |                            |                         |
|    | ASSORBIMENTO ACQUA IN %<br>% WATER ABSORPTION                                                       | UNI EN ISO 10545/3      | ≤ 0,5 %                                                                                       |                            | CONFORME<br>COMPLIANT   |
|    | FORZA DI ROTTURA<br>BREAKING STRENGTH                                                               |                         | > 1300 N                                                                                      |                            | > 1350 N                |
|                                                                                       | MODULO DI ROTTURA – MODULUS OF RUPTURE<br>NOT APPLICABLE TO TILES WITH BREAKING<br>STRENGTH ≥3000 N | UNI EN ISO 10545/4      | ≥ 35 N/MM²                                                                                    |                            | ≥ 45*<br>*average value |
|    | RESISTENZA ALL'ABRASIONE<br>RESISTANCE TO SURFACE ABRASION                                          | UNI EN ISO 10545/7      | PEI<br>Solo per piastrelle smaltate<br>Only for glazed tiles                                  |                            | PEI 4                   |
|    | RESISTENZA AGLI SBALZI TERMICI<br>THERMAL SHOCKS RESISTANCE                                         | UNI EN ISO 10545/9      | NESSUN CAMPIONE DEVE<br>PRESENTARE DIFETTI VISIBILI<br>NO SAMPLE MUST SHOW<br>VISIBLE DEFECTS |                            | CONFORME<br>COMPLIANT   |
|   | RESISTENZA AL GELO<br>FROST RESISTANCE                                                              | UNI EN ISO 10545/12     | RESISTENTI - RESISTANT                                                                        |                            | CONFORME<br>COMPLIANT   |
|  | RESISTENZA ALL'ATTACCO CHIMICO<br>HOUSEHOLD CHEMICALS RESISTANCE                                    | UNI EN ISO 10545-13     | RESISTENTI - RESISTANT                                                                        |                            | CONFORME<br>COMPLIANT   |
|  | RESISTENZA ALLE MACCHIE<br>STAIN RESISTANCE                                                         | UNI EN ISO 10545/14     | GL ≥ 3                                                                                        |                            | Classe 3                |
|  | SCIVOLOSITÀ<br>SLIP RESISTANCE                                                                      | DIN 51130               | Dichiarare un valore (R)<br>Declare a value (R)                                               |                            | R10 – R11               |
|  | RESISTENZA AL FUOCO<br>FIRE RESISTANCE                                                              | UNI EN ISO 13501/1      | CLASSE A1 OPPURE A1 <sub>FL</sub><br>CLASS A1 OR A1 <sub>FL</sub>                             |                            | A1 <sub>FL</sub>        |

CERAMICHEitaliane®

Via Radici Nord, 126 - 42014 Castellarano RE ITALY  
Telefono +39 0536 071078 - Fax +39 0536 077121 - [segreteria@ceritaliane.it](mailto:segreteria@ceritaliane.it) - [www.ceritaliane.it](http://www.ceritaliane.it)

made in  Italy