



CEMENTOS ALFA, S.A.

PLANT: MATAPORQUERA

ER Certificate: ER-0572/1998



TECHNICAL CHARACTERISTICS CERTIFICATE

Cement

CEM I 52,5 N (ma)

Period

May, 2026

CE: 0099/CPR/A33/1148

TESTS	Results Average Value	Standard Spec. EN/UNE
Chemical Characteristics		
Loss on Ignition %	2,4	< 5,0
Insoluble Residue %	0,9	< 5,0
Sulphates (SO ₃) %	3,2	< 4,0
Chlorides %	0,05	< 0,10
Physical and Mechanical Characteristics		
Normal Consistency Water %	30,7	
Initial Setting Time min	164	> 45
Final Setting Time min	206	< 720
Soundness Le Chatelier mm	0,2	< 10
Specific Surface (Blaine) cm ² /g	4477	
Compressive Strength at 2 days MPa		
• Monthly average	34,8	> 20,0
• Cumulative average (06/2025 - 05/2026)	35,6	> 20,0
• Cumulative Std. Dev. (06/2025 - 05/2026)	1,5	
Compressive Strength at 28 days MPa		
• Monthly average	63,5	> 52,5
• Cumulative average (06/2025 - 05/2026)	61,4	> 52,5
• Cumulative Std. Dev. (06/2025 - 05/2026)	1,6	
Additional Characteristics		
Alkali Equivalent (%)	0,64	< 0,75

This document doesn't imply that any amount of cement has been supplied by the Company

Barrio la Estación, s/n.
39410 Mataporquera (Cantabria)
Tel. 942 770 058
Fax 942 770 243
info@alfainforma.com
www.valderrivas.es

Chief of Quality Control

