

TEST REPORT PREPARED FOR DRAGON PORTLAND CEMENT

REPORT REFERENCE	DG 71
CLIENT REFERENCE	DAC/01/ 05- 06 CEMI 52.5N
SAMPLE	CEM I 52.5R
SEAL NUMBER	B445103
SAMPLE DATE	11-Sep-25
SAND	GERMAN
DATE OF RECEIPT OF SAMPLE	15-Sep-25
DATE OF TESTS	15-Sep-25 to 13-Oct-25
DATE OF REPORT	13-Oct-25

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	157 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------


COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	35.3 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	61.4 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	2.85 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.34 %	(BSEN 196-2:2013)
SULPHATE	3.12 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**