

TEST REPORT PREPARED FOR DRAGON PORTLAND CEMENT

REPORT REFERENCE	DG	76
CLIENT REFERENCE	DAC/01/ 04-06 CEM1 52.5N	
SAMPLE	CEM I 52.5R	
SEAL NUMBER	B445157	
SAMPLE DATE	10-Jul-26	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	15-Jul-26	
DATE OF TESTS	16-Jul-26	to 13-Aug-26
DATE OF REPORT	13-Aug-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	182 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	37.5 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	66.4 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	2.73 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.36 %	(BSEN 196-2:2013)
SULPHATE	2.92 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician

Date

29.09.21