

TEST REPORT PREPARED FOR DRAGON PORTLAND CEMENT

REPORT REFERENCE	DG	69
CLIENT REFERENCE	DAC/01/ 03- 25 CEMI 52.5N	
SAMPLE	CEM I 52.5R	
SEAL NUMBER	B335431	
SAMPLE DATE	22-May-25	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	28-May-25	
DATE OF TESTS	28-May-25	to 25-Jun-25
DATE OF REPORT	26-Jun-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	206 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	39.0 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	68.4 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	2.88 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.72 %	(BSEN 196-2:2013)
SULPHATE	3.09 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician

Date **29.09.21**