

## TEST REPORT PREPARED FOR DRAGON PORTLAND CEMENT

REPORT REFERENCE	DG	69
CLIENT REFERENCE	DAC/14/03- 25 CEM II/A-L 42.5R	
SAMPLE	CEM 11 42.5R A-L	
SEAL NUMBER	B335434	
SAMPLE DATE	22-May-25	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	28-May-25	
DATE OF TESTS	28-May-25	to 25-Jun-25
DATE OF REPORT	26-Jun-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

### INITIAL SETTING TIME

INITIAL SETTING TIME	232 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

### COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	32.3 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	57.1 MPa	(Mean of 6 results, none discarded)

### CHEMICAL COMPOSITION :- by mass, as received

LOI	N/A %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	N/A %	(BSEN 196-2:2013)
SULPHATE	2.95 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**  
Senior Technician

Date **29.09.21**