

## TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	483
CLIENT REFERENCE	CPC/DAC/119-25 26-3-25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	09-Apr-25	
DATE OF TESTS	09-Apr-25	to 07-May-25
DATE OF REPORT	08-May-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

### INITIAL SETTING TIME

INITIAL SETTING TIME	206 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

### COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	37.6 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	61.0 MPa	(Mean of 6 results, none discarded)

### CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	2.90 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**  
Senior Technician