

TEST REPORT PREPARED FOR DRAGON CEMENT

| | | |
|---------------------------|-----------------------|--------------|
| REPORT REFERENCE | DG 42 | 484 |
| CLIENT REFERENCE | CPC/DAC/121-25 2-4-25 | |
| SAMPLE | CEM II A-L 42.5R | |
| SAND | GERMAN | |
| DATE OF RECEIPT OF SAMPLE | 15-Apr-25 | |
| DATE OF TESTS | 15-Apr-25 | to 13-May-25 |
| DATE OF REPORT | 13-May-25 | |

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

| | | |
|----------------------|----------|-------------------|
| INITIAL SETTING TIME | 184 mins | (BSEN 196-3:2016) |
|----------------------|----------|-------------------|

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

| | | |
|------------|----------|-------------------------------------|
| AT 2 DAYS | 33.1 MPa | (Mean of 6 results, none discarded) |
| AT 28 DAYS | 56.7 MPa | (Mean of 6 results, none discarded) |

CHEMICAL COMPOSITION :- by mass, as received

| | | |
|-------------------|--------|-------------------|
| LOI | n/a % | (BSEN 196-2:2013) |
| INSOLUBLE RESIDUE | n/a % | (BSEN 196-2:2013) |
| SULPHATE | 3.28 % | (BSEN 196-2:2013) |
| | | |

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician