

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	487
CLIENT REFERENCE	CPC/DAC/127-25 30-4-25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	01-May-25	
DATE OF TESTS	06-May-25	to 03-Jun-25
DATE OF REPORT	04-Jun-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	208 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	30.1 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	54.5 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	3.15 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician