

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	492
CLIENT REFERENCE	CPC/DAC/139 11-06-25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	12-Jun-25	
DATE OF TESTS	12-Jun-25	to 10-Jul-25
DATE OF REPORT	10-Jul-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	192 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	33.1 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	54.7 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	3.02 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician