

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	512
CLIENT REFERENCE	CPC/DAC/185 19/11/25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	26-Nov-25	
DATE OF TESTS	26-Nov-25	to 24-Dec-25
DATE OF REPORT	06-Jan-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	174 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	31.5 MPa	(Mean of 6 results, none discarded)
-----------	----------	-------------------------------------

AT 28 DAYS	56.6 MPa	(Mean of 6 results, none discarded)
------------	----------	-------------------------------------

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
-----	-------	-------------------

INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
-------------------	-------	-------------------

SULPHATE	3.03 %	(BSEN 196-2:2013)
----------	--------	-------------------

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician