

## TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	513
CLIENT REFERENCE	CPC/DAC/181 03/11/25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	26-Nov-25	
DATE OF TESTS	26-Nov-25	to 24-Dec-25
DATE OF REPORT	06-Jan-26	

### ALL RESULTS RELATE ONLY TO SAMPLE TESTED

#### INITIAL SETTING TIME

INITIAL SETTING TIME	170 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

#### COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	31.1 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	58.0 MPa	(Mean of 6 results, none discarded)

#### CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	3.03 %	(BSEN 196-2:2013)

## END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician