

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	529
CLIENT REFERENCE	CPC/DAC/221 14/4/26	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	20-Apr-26	
DATE OF TESTS	21-Apr-26	to 19-May-26
DATE OF REPORT	19-May-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	197 mins	(BS EN 196-3:2016)
----------------------	----------	--------------------


COMPRESSIVE STRENGTH: MORTAR PRISMS (BS EN 196-1:2016).

AT 2 DAYS	33.9 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	59.6 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BS EN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BS EN 196-2:2013)
SULPHATE	2.97 %	(BS EN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician