

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	531
CLIENT REFERENCE	CPC/DAC/225 29/4/26	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	05-May-26	
DATE OF TESTS	06-May-26	to 03-Jun-26
DATE OF REPORT	04-Jun-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	202 mins	(BS EN 196-3:2016)
----------------------	----------	--------------------


COMPRESSIVE STRENGTH: MORTAR PRISMS (BS EN 196-1:2016).

AT 2 DAYS	31.3 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	61.5 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BS EN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BS EN 196-2:2013)
SULPHATE	2.90 %	(BS EN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician