

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	540
CLIENT REFERENCE	CPC/DAC/247 15/7/26	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	20-Jul-26	
DATE OF TESTS	20-Jul-26	to 17-Aug-26
DATE OF REPORT	17-Aug-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	211 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	28.5 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	56.6 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	2.96 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician