PARKHOUSE ENTERPRISE LTD
Independent consultants & specialist materials suppliers

3 Dunstan Hill
Kirton in Lindsey
Gainsborough
Lincolnshire
DN21 4FG

T: 01652 656931
E: office@parkhouseent.co.uk

| TEST REPORT PREPARED FOR DRAGON CEMENT | | | |
|---|---|---|---|
| REPORT REFERENCE | DG 42 544 | | |
| CLIENT REFERENCE | CPC/DAC/255 NO DATE ON SAMPLE CERT | | |
| SAMPLE | CEM II A-L 42.5R | | |
| SAND | GERMAN | | |
| DATE OF RECEIPT OF SAMPLE | 14-Aug-26 | | |
| DATE OF TESTS | 17-Aug-26 | to | 14-Sep-26 |
| DATE OF REPORT | 15-Sep-26 | | |
| ALL RESULTS RELATE ONLY TO SAMPLE TESTED | | | |

| INITIAL SETTING TIME | | | |
|---|---|---|---|
| INITIAL SETTING TIME | 163 | mins | (BSEN 196-3:2016) |

| COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016). | | | |
|---|---|---|---|
| AT 2 DAYS | 32.0 | MPa | (Mean of 6 results,none discarded) |
| AT 28 DAYS | 58.5 | MPa | (Mean of 6 results,none discarded) |

| CHEMICAL COMPOSITION :- by mass, as received | | | |
|---|---|---|---|
| LOI | n/a | % | (BSEN 196-2:2013) |
| INSOLUBLE RESIDUE | n/a | % | (BSEN 196-2:2013) |
| SULPHATE | 3.00 | % | (BSEN 196-2:2013) |
| | | | |

**END OF REPORT**

SIGNED:.....

**Certificate signed by:** S.Sykes
Senior Technician