

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	516
CLIENT REFERENCE	CPC/DAC/191 SILO 1 10/12/25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	12-Dec-26	
DATE OF TESTS	15-Dec-25	to 12-Jan-26
DATE OF REPORT	12-Jan-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	203 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	27.2 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	57.3 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	2.78 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician