

## TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	517
CLIENT REFERENCE	CPC/DAC/193 SILO 1 18/12/25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	22-Dec-25	
DATE OF TESTS	22-Dec-25	to 19-Jan-26
DATE OF REPORT	19-Jan-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

### INITIAL SETTING TIME

INITIAL SETTING TIME	190 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

### COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	30.9 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	59.8 MPa	(Mean of 6 results, none discarded)

### CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	2.90 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician