

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	500
CLIENT REFERENCE	CPC/DPL/157 13/8/25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	18-Aug-25	
DATE OF TESTS	18-Aug-25	to 15-Sep-25
DATE OF REPORT	16-Sep-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	199 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------


COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	28.9 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	56.8 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BSEN 196-2:2013)
SULPHATE	3.06 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician